

PATENT APPLICATION
Navy Case No. 83,517

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICATION FOR LETTERS PATENT

TO ALL WHOM IT MAY CONCERN:

BE IT KNOWN THAT Eric Houser and Robert McGill of
Nokesville, VA and Lorton, VA, who are citizens of the United
States of America and the United Kingdom, respectively, has
invented certain new and useful improvements in "HYPERBRANCHED
CHEMOSELECTIVE SILICON-BASED POLYMERS FOR CHEMICAL SENSOR
APPLICATIONS" of which the following is a specification:

Please Contact Preparer:
Philip E. Ketner
Reg. No. 46,272
Tel: 202-404-1554

Hyperbranched Chemoselective Silicon-Based Polymers for Chemical Sensor Applications

BACKGROUND OF THE INVENTION

Field of the Invention

[0001] The present invention relates to the detection of noxious chemical species by means of chemoselective hyperbranched polymeric compounds. More particularly, the invention relates to the detection of toxic or explosive chemical vapors, such as chemical agents or nitro-substituted species, respectively, by sorbent materials comprising chemoselective hyperbranched polymeric molecules.

Description of Related Art

[0002] Determining and/or monitoring the presence of certain chemical species within an environment, e.g., pollutants, toxic substances and other predetermined compounds, is becoming of increasing importance with respect to such fields as health, environmental protection, resource conservation, and chemical processes. Devices for the molecular recognition of noxious species or other analytes typically include (1) a substrate and (2) a molecular recognition coating upon the substrate. These devices may be used, for example, in chemical vapor sensing or the selective separation of gases by gas chromatography. Small molecular recognition devices are described in Grate et al., *Sensors and Actuators B*, 3, 85-111 (1991) and Grate et al., *Analytical Chemistry*, Vol. 65, No. 14, Jul. 15, 1993, both of which are incorporated herein by reference.

[0003] Frequently, the substrate is a piezoelectric material or a waveguide, which can detect small changes in mass. One illustrative example of a device relying upon molecular recognition as a surface is known as a surface acoustic wave (SAW) sensor. SAW devices function by generating mechanical surface waves on a thin slab of a piezoelectric material, such as quartz, that oscillates at a characteristic resonant frequency when placed in a feedback circuit with a radio frequency amplifier. The oscillator frequency is measurably altered by small changes in mass and/or elastic modulus at the surface of the SAW device.

[0004] SAW devices can be adapted to a variety of gas-phase analytical problems by designing or selecting specific coatings for particular applications. The use of chemoselective polymers for chemical sensor application is well established as a way to increase the sensitivity and selectivity of a chemical sensor with respect to specific classes or types of analytes. Typically, a chemoselective polymer is designed to contain functional groups that can interact preferentially with the target analyte through dipole-dipole, Van der Waal's, or hydrogen bonding forces. For example, strong hydrogen bond donating characteristics are important for the detection of species that are hydrogen bond acceptors, such as toxic organophosphorus compounds. Increasing the density of hydrogen bond acidic binding sites in the coating of a sensor results in an increase in sensitivity.

[0005] Chemoselective films or coatings used with chemical sensors have been described by McGill et al. in *Chemtech*, Vol. 24, No. 9, 27-37 (1994). The materials used as the chemically active, selectively absorbent layer of a molecular recognition device have often been polymers, as described in Hansani in *Polymer Films in Sensor Applications* (Technomic, Lancaster, Pa. 1995). For example, Ting et al. investigated polystyrene substituted with hexafluoroisopropanol (HFIP) groups for its compatibility with other polymers in *Journal of Polymer Science: Polymer Letters Edition*, Vol. 18, 201-209 (1980). Later, Chang et al. and Barlow et al. investigated a similar

1 material for its use as a sorbent for organophosphorus vapors, and examined its behavior on a bulk quartz crystal
2 monitor device in *Polymer Engineering and Science*, Vol. 27, No. 10, 693-702 and 703-15 (1987). Snow et al. (*NRL*
3 *Letter Report*, 6120-884A) and Sprague et al. (*Proceedings of the 1987 U.S. Army Chemical Research Development*
4 *and Engineering Center Scientific Conference on Chemical Defense Research*, page 1241) reported making
5 materials containing HFIP that were based on polystyrene and poly(isoprene) polymer backbones, where the HFIP
6 provided strong hydrogen bond acidic properties. These materials were used as coatings on molecular recognition
7 devices, such as SAW sensors, and showed high sensitivity for organophosphorus vapors. However, both the parent
8 polymers and the HFIP-containing materials were glassy or crystalline at room temperature. Because vapor
9 diffusion may be retarded in glassy or crystalline materials, the sensors produced were slow to respond and recover.
10 Further, these are polymeric materials and, like all polymers, they can vary significantly from batch to batch in
11 precise composition, purity and yield. Additional information is reported in *Polym. Eng. Sci.*, 27, 693 and 703-715
12 (1987).

13 [0006] Vicari et al., U. S. Patent No. 6,114,489, issued September 5, 2000, discloses reactive hyper-
14 branched polymers containing terminal hydroxy, carboxy, epoxy, and isocyanate groups. The compounds are useful
15 as components in powder coating compositions for the formation of hard, impact resistant films. Examples of the
16 preferred hyperbranched polyesters are those formed from α,α -bis(hydroxymethyl)-propionic acid. The backbone
17 of these hyperbranched polymers are composed of polyester units.

18 [0007] Okawa et al., U.S. patent No. 6,140,525 issued October 31, 2000, discloses a class of
19 hyperbranched polymers that are prepared by contacting macromonomers that have both silicon hydride and
20 unsaturated organic terminal groups with group VIII metal catalysts. The hyperbranched polymers are useful as
21 surfactants, gelling agents, drug delivery systems, and polymeric absorbents. The hyperbranched polymer
22 backbones are comprised of a combination of siloxane and carbosilane segments. Examples of preferred macro-
23 monomers include $(\text{HSi}(\text{CH}_3)_2\text{O})_2\text{Si}(\text{CH}_3)\text{OSi}(\text{CH}_3)_2(\text{CH}_2)_2(\text{Si}(\text{CH}_3)_2\text{O})_n\text{Si}(\text{CH}_3)_2\text{CH}=\text{CH}_2$, where n is 10 to 100.

24 [0008] Decker et al., U.S. Patent No. 6,001,945, issued December 14, 2001, discloses hyperbranched
25 polymers containing silicon atoms and a method of making these materials. The exchange (condensation) reaction
26 that forms the hyperbranched polymers results in the elimination of an alcohol by-product and the formation of
27 hyperbranched polymer backbones comprised of siloxane linkages.

28 [0009] The inventors have now discovered a class of hyperbranched molecules that can be used to
29 produce hydrogen bond acidic coatings for chemical sensor applications. Using the hyperbranched molecules that
30 are highly functionalized results in significant sensitivity improvements. Further, the chemoselective hyper-
31 branched molecules of the present invention exhibit, not only improved sensitivity to organophosphorus species, but
32 also high selectivity and sensitivity toward nitro-substituted chemical vapors, and are thus also useful for detecting
33 the presence of explosives. Conventional explosives, such as trinitrotoluene (TNT), hexahydro-1,3,5-trinitro-1,3,5-
34 triazine (RDX), and octahydro-1,3,5-trinitro-1,3,5,7-tetrazocine (HMX), may be contained in unexploded munitions,
35 e.g., buried below the surface of the ground. Such munitions exude or leak vapors of the explosive. These vapors
36 are typically concentrated in the surrounding soil and then migrate to the surface where they can be detected by the
37 compounds, devices and methods of the invention.

SUMMARY OF THE INVENTION

[0010] According to a first aspect of the present invention, there is provided a hyperbranched polymeric compound having; (1) a polymer backbone portion that is at least partly randomly branched; (2) at least one pendant group extending from the polymer backbone portion; (3) and at least one halogen substituted alcohol or phenol group substituted at the pendant group(s) of the polymer backbone portion.

[0011] According to a second aspect of the invention, there is provided a device for selective molecular detection, the device comprising a sensing portion, wherein the sensing portion includes a substrate having coated thereon a layer, the layer comprising the hyperbranched compound of the invention.

According to another aspect of the invention, there is provided a method of detecting a hydrogen bond accepting vapor, such as a nitroaromatic vapor, comprising the steps of:

- (a) contacting the molecules of such a vapor with the sensing portion of the device of the invention;
- (b) collecting the molecules in the layer of the device, the molecules altering a specific physical property of the layer; and
- (c) detecting the amount of change with respect to the physical property from before the contacting step (a) and after the collecting step (b).

According to yet another aspect of the invention, there is provided a solution for preparing a chemical vapor sensor comprising (a) an amount of the hyperbranched compound of the invention effective to enhance the sensitivity of the sensor to hydrogen bond accepting vapors such as chemical agents or nitroaromatic compounds and (b) a solvent for the hyperbranched compound.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] Fig. 1 shows an example of a hyperbranched compound of the invention, here, a hyperbranched polycarbosilane with fluoroalcohol functionalized allyl groups.

[0013] Fig. 2 shows another example of a hyperbranched compound of the invention, here, a hyperbranched polycarbosilane with fluoroalcohol functionalized phenyl and allyl groups.

DETAILED DESCRIPTION OF THE INVENTION

[0014] The hyperbranched molecules of the invention are polymeric molecular constructions having a randomly branched backbone portion with attached pendant groups. The randomly branched backbone portion of the molecule may be composed of linear, branched, and dendritic units, which may themselves be further branched, forming the backbone portion of the hyperbranched polymer molecule. The detailed chemical structure of the hyperbranched backbone may dominate certain polymer physical properties. Hyperbranched polymers may be distinguished from dendritic, branched, and linear polymers in that:

- (a) The degree and distribution of branching in a hyperbranched polymer is variable and, therefore, the molecular weight of the hyperbranched materials usually occurs over a broad distribution while a dendrimer has a precise structure and molecular weight;


(b) The chemical synthesis of a hyperbranched polymer may be carried out in a single step from the starting monomer, whereas the synthesis of a dendritic polymer requires a multistep synthetic procedure;

(c) Linear polymers are not branched; and

(d) Branched polymers are branched in a regular fashion whereas hyperbranched polymers are branched in a random fashion.

[0015] Although not bound by theory, it is believed that the hyperbranched morphology offers advantages over linear macromolecules with the same or similar repeating units because the randomly branched structure imposes particular physical properties such as reduced polymer chain entanglement, lower glass transition and melting temperatures and increased availability of terminal functional groups. These constraints, often including steric crowding, inhibit even very long chains from packing in their thermodynamically preferred conformations for crystallization, and thereby lower their melting points due to entropic factors. The random variation in structure that occurs with hyperbranched materials is also a contributing factor to the bulk properties of these materials. By controlling the structure of the hyperbranched polymer, for example, with suitable ratios of branching arm length to average branch multiplicity, the free volume available to the chain ends can be made relatively large. In this case, a large free volume at the chain ends may facilitate arm segmental motion, although this effect is often negated by steric crowding at the terminal groups.

[0016] The compound of the invention is a hyperbranched polymeric compound having; (1) a polymer backbone portion that is at least partly randomly branched; (2) at least one pendant groups extending from the polymer backbone portion; (3) and at least one halogen substituted alcohol or phenol group substituted at the pendant group(s) of the polymer backbone portion. The compound may be entirely organic or organometallic in composition. Preferred compounds can be represented by the general formula:



wherein A is the hyperbranched backbone portion of the polymer;

L and M are independently selected pendant groups of the polymer backbone;

X and Y are independently selected halogen substituted alcohol or phenol groups;

q and r are independently selected and at least 1, preferably ranging from 1 to about 10; and

n is at least 3, preferably ranging from 20 to 100,000.

[0017] A, the hyperbranched backbone portion of the compound, may be composed of repeating units consisting of a single atom such as a carbon or silicon atom; a hydrocarbon moiety; an organometallic fragment or cluster; or a silicon based moiety such as a siloxane, carbosilane, or silylene moiety; or a combination thereof. Examples of useful "A" backbone repeat units include $\{\text{Si}(-\text{Z})_x\}$, $\{\text{C}(-\text{Z})_x\}$, $\text{Fe}(-\text{C}_5\text{H}_4\text{Z}-)_2$, $\text{C}_6\text{H}_n(-\text{Z})_{6-n}$, and the like, wherein Z is a hydrocarbon, silylene, carbosilane, siloxane, or carbosiloxane fragment of 1 to 20 atoms in length, including but not limited to alkylene, alkenylene, alkynylene, cycloalkylene, cycloalkenylene, arylene, or

heterocyclene. Preferably, however, A is {Si-(alkylene-)}, {Si-(arylene-)}, or {Si-(alkenylene-)}. Most preferably, A is {Si[(CH₂)_x]} wherein x is 1 to 3.

[0018] L and M in the above formula are independently selected pendant groups that extend from the hyperbranched backbone portion of the compound. L or M may be saturated or unsaturated. By "unsaturated" is meant any site of unsaturation, such as, for example, a double or triple bond or an aromatic ring. L or M may be entirely hydrocarbon or may contain one or more heteroatoms, such as, for example, Si, N, O, S, F, Cl, Br and the like, and may contain further branching entities. For example, L or M may independently be alkylene, alkenylene, alkynylene, arylene, alkylene-arylene, alkenylene-arylene, alkynylene-arylene, -C-(alkenylene)₃, -Si-(alkenylene-)₃, -N-(alkenylene-)₂, or -SiO-(alkenylene-)₃, where alkenylene is as defined above; -C-[alkylene-Si-(alkenylene)₃]₃, -Si-[alkylene-C-(alkenylene)₃]₃, -Si-[alkylene-Si-(alkenylene)₃]₃, -SiO-[alkylene-Si-(alkenylene)₃]₃, -CO-[alkylene-Si-(alkenylene)₃]₃, -Si-[alkylene-N-(alkenylene)₂]₃, where alkylene and alkenylene are defined as above; -C-(cycloalkenylene-)₃, -Si-(cycloalkenylene-)₃, and CON-(cycloalkenylene-)₃, where cycloalkenylene is defined as above; -C-[cycloalkylene-Si-(alkenylene)₃]₃, -Si-[cycloalkylene-C-(alkenylene)₃]₃, -Si-[cycloalkylene-Si-(alkenylene)₃]₃, -SiO-[cycloalkylene-Si-(alkenylene)₃]₃, -CO-[cycloalkylene-Si-(alkenylene)₃]₃, -Si-[cycloalkylene-N-(alkenylene)₂]₃, where cycloalkylene and alkenylene are defined as above; -C-(arylene-)₃, -Si-(arylene-)₃, and -SiO-(arylene-)₃, where arylene is defined as above; -C-(heterocyclene-)₃, -Si-(heterocyclene-)₃, and -SiO-(heterocyclene-)₃, where heterocyclene is as defined above; -C-[alkylene-Si-(alkylene-arylene)₃]₃, -Si-[alkylene-C-(alkylene-arylene)₃]₃, -Si-[alkylene-Si-(alkylene-arylene)₃]₃, -SiO-[alkylene-Si-(alkylene-arylene)₃]₃, -CO-[alkylene-Si-(alkylene-arylene)₃]₃, -Si-[alkylene-N-(alkylene-arylene)₂]₃, where alkylene or arylene are defined as above.

[0019] Preferably, however, L and M are independently an alkenylene, alkylene-arylene, alkenylene-arylene, -[alkylene-Si-(alkenylene)₃]₃ or an -[alkylene-Si-(alkylene-arylene)₃]₃ group. Even more preferably, L and M are independently -(CH₂)_m-, -(CH=CH-CH₂)-, -[(CH₂)_mC₆H₄]-, -[(CH₂)_m-Si-(CH=CH-CH₂-)]₃ or -Si-[(CH₂)_m-Si-(CH₂)_n-C₆H₄]₃ wherein m and n are independently 1 to 6.

[0020] The novel compounds of the invention are strongly hydrogen bond donating. They are useful in a variety of applications, especially as a coating material on chemical sensors. They are very sensitive for hydrogen bond accepting vapors such as organophosphorus and nitro-substituted compounds such as those in a great number of well-known toxic and explosive materials, respectively.

[0021] The compounds of the invention can be synthesized by reacting hexafluoroacetone with the parent hyperbranched molecule, comprising a hyperbranched backbone A and a number of pendant unsaturated groups, taking advantage of the reactivity of perfluoroketones with terminally unsaturated groups, as described by Urry et al., *J. Org. Chem.*, **1968**, *33*, 2302-2310, hereby incorporated by reference. Alternatively, the compounds of the invention can be synthesized by reacting hexafluoroacetone with the parent hyperbranched molecule, comprising a hyperbranched backbone A and a number of pendant groups containing metalated sites, followed by protonation, as described by Barbarich et al., *J. Am. Chem. Soc.*, **1999**, *121*, 4280-4281, hereby incorporated by reference. Two such hyperbranched compounds of the invention are shown in Figs. 1 and 2. Using known methods (see, for example, Whitmarsh, C. K., Interrante, L. V. *Organometallics*, **1991**, *10*, 1336-1344; Uhlig, W. J. *Polym. Sci., Part*

1 A: *Polym. Chem.*, **1998**, 36, 725-735 and Koopman, F., Frey, H. *Macromolecules* **1996**, 29, 3701-3706.) these
2 compounds are typically synthesized in moderate to high yield.

3 [0022] Once synthesized, these functionalized hyperbranched compounds can be coated to a controlled
4 film thickness on a substrate, either alone or mixed with a solvent or similarly functionalized molecule. Useful
5 substrates include planar chemical sensors, such as surface acoustic wave (SAW) substrates; silica optical fibers;
6 microcantilevers and other MEMS devices, and the interior surfaces of silica capillaries. The substrate chosen is
7 based on the sensing mechanism being used.

8 [0023] The principle of operation of an acoustic wave device transducer involves the production of an
9 acoustic wave that is generated on the surface or through the bulk of a substrate material and allowed to propagate.
10 To generate an acoustic wave typically requires a piezoelectric material. Applying a time varying electric field to
11 the piezoelectric material will cause a synchronous mechanical deformation of the substrate with a coincident
12 generation of an acoustic wave in the material. The time varying electric field is generated in the surface by
13 applying a time varying electrical field through one or more electrodes, which are connected to the piezoelectric
14 material via one or more metal wire bonds and to an electrical circuit. Another electrode or electrodes receives the
15 wave at a distance from the first electrode or electrodes. The second electrode or electrodes is also connected via
16 metal wire bonds to the electrical circuit and the piezoelectric material. Such devices are operable in a frequency
17 range of about 2 kilohertz to 10 gigahertz, preferably from about 0.2 megahertz to about 2 gigahertz and, more
18 preferably, in the range of between about 200 to 1000 megahertz.

19 [0024] For piezoelectric sensors, piezoelectric substrates well-known in the art, such as ST-cut quartz, are
20 useful in accordance with the invention. In addition to quartz crystals, piezoelectric ceramics, such as those of the
21 barium titanate and lead zirconium titanate families, are suitable substrates. These include, for example, LiNbO_3 ;
22 BaTiO_3 ; 95 wt.% BaTiO_3 /5% GaTiO_3 ; 80 wt.% BaTiO_3 /12% PbTiO_3 /8% CaTiO_3 ; PbNb_2O_6 ; $\text{Na}_0.5\text{K}_{0.5}\text{NbO}_3$;
23 $\text{Pb}_{0.94}\text{Sr}_{0.06}(\text{Ti}_{0.48}\text{Sr}_{0.52})\text{O}_3$; and $\text{Pb}_{0.94}(\text{Ti}_{0.48}\text{Sr}_{0.52})\text{O}_3$. In some cases, the substrate may comprise a piezoelectric
24 coating material, such as ZnO or AlN, applied to a non-piezoelectric material, such as silicon. The piezoelectric
25 properties of these and other suitable materials are provided in *CRC Handbook of Materials Science*, Vol. III,
26 Charles T. Lynch, CRC Press: Boca Raton, 198 (1975).

27 [0025] The sensing portion of an acoustic wave device of the invention is the area under the
28 chemoselective layer where the chemoselective layer covers the transducer. The area of the sensing portion of such
29 a device can be on the order of cm^2 to μm^2 .

30 [0026] An optical waveguide chemical sensor consists of a light source, an optical waveguide, a
31 chemoselective film or layer, and a detector to analyze the light after interacting with the layer. The waveguide is
32 used to propagate light to a sensing portion of the device that contains the chemoselective layer. The light travels
33 towards this coating and interacts with it. If the analyte being detected is present in the layer, the optical
34 characteristics of the light may be altered, and the change is detected by an optically sensitive detector.

[0027] Useful optical chemical sensors, commonly referred to as optrodes, typically include light sources such as semiconductor lasers, light-emitting diodes, or halogen lamps; optical waveguides such as fiber optics or planar waveguide substrates; chemoselective layers deposited on the sensing portion of the optrode exposed to an analyte; and detectors for monitoring the optical characteristics of an optrode. Sorption of the analyte to the chemoselective layer modifies the optical characteristics of the optrode, and this is usually detected as a change in refractive index or light intensity at one or more wavelengths of light. Thus, for optical sensors, both optical fibers and optical wave-guides are well-known in the art and useful in the present invention.

[0028] Fiber optic waveguides for sensor applications are commonly manufactured from silica glass or quartz as the core of the fiber. Surrounding this core is a cladding material that exhibits a lower refractive index than the core to achieve internal reflectance. Chemoselective layers are typically applied at the distal tip of a fiber optic or along the side of the fiber optic where a portion of the cladding material has been removed.

[0029] Planar waveguide optical sensors use planar substrate devices as light guides. The use of a planar waveguide normally involves the use of evanescent wave techniques to take advantage of the large active surface area available. Many of these sensors use the fluorescent properties of a chemoselective layer and are thus called Total Internal Reflection Fluorescence (TIRF) sensors.

[0030] Preferably, acoustic wave devices are used as the substrate for the device of the invention. Particularly preferred are SAW devices such as 915 MHz two-port resonators made of ST-cut quartz with aluminum metallization and a thin silicon dioxide overcoat. SAW resonators and oscillator electronics to drive them are commercially available from RFM, Dallas, Texas.

[0031] Before applying a coating to form the sensor portion of the device of the invention, the substrate is usually cleaned. The cleaning procedure typically involves rinsing the device in an organic solvent and then subjecting it to plasma cleaning, as is well-known. Optionally, the substrate can be silanized with a material such as diphenyltetramethyldisilazane (DPTMS) by immersing the cleaned substrate surface in liquid DPTMS and then placing the immersed surface into a partially evacuated chamber heated to about 170°C for about 12 hours. The silanized substrate is then removed and solvent cleaned with, for example, toluene, methanol, chloroform, or a physical or serial combination thereof, before applying the chemically sensitive sensor layer of the device.

[0032] The method used for coating the compounds of the invention onto a substrate is not critical, and various coating methods known in the art may be used. Typically, the coating is applied to the substrate in solution, either by dipping, spraying or painting, preferably by an airbrush or spin coating process. Laser deposition techniques may also be used, particularly when coating MEMS devices. The concentration of the compound of the invention in the coating solution should be sufficient to provide the viscosity most appropriate for the selected method of coating, and may easily be determined empirically.

[0033] The solvent used, although not critical, should be sufficiently volatile as to facilitate quick and easy removal, but not so volatile as to complicate the handling of the coating solution prior to being deposited on the substrate. Examples of useful organic solvents include, for example, hexane, chloroform, dichloromethane, toluene, xylenes, acetonitrile and tetrahydrofuran. J.W. Grate and R.A. McGill in *Analytical Chemistry*, Vol. 67, No. 21, 4015-19 (1995), the subject of which is hereby incorporated by reference, describe making chemical acoustic wave

1 detectors by applying a thin film to a surface acoustic wave device. The thickness of the chemoselective layer
2 preferably does not exceed that which would reduce the frequency of a chemical sensor operating at 250 megahertz
3 by about 250 kilohertz and, typically, is in the range of about 0.5 nm to 10 microns, preferably in the range of 5 to
4 500 nm.

5 [0034] The coating may comprise a single layer or multiple layers. With multiple layers, a layer
6 containing the compound of the invention may be combined with at least one other layer that provides pores suitable
7 for physically eliminating some chemical species of large size that are not to be monitored.

8 [0035] The process of sorption plays a key role in the performance of chemical sensors for gas phase
9 analysis. For example, microsensors, which consist of a physical transducer and a selective sorbent layer, sense
10 changes in the physical properties, such as mass, of the sorbent layer on the surface of the transducer, due to the
11 sorption of analyte molecules from the gas phase into the sorbent layer. Coating properties that are known to elicit a
12 detectable SAW sensor response are mass (i.e., as determined by the thickness and density of the coating), elasticity,
13 viscoelasticity, conductivity, and dielectric constant. Changes in these properties can also result in changes in the
14 attenuation (i.e., loss of acoustic power) of the wave. In some situations, monitoring the attenuation may be
15 preferable to monitoring the velocity of a wave. Alternatively, there are some situations where simultaneously
16 monitoring both velocity and attenuation can be useful. In any event, it is the modification of the sensed properties
17 of the sorbent layer, as a result of sorption, that results in the detection of analyte molecules in the gas phase. SAW
18 devices coated with compounds of the invention are capable of detecting mass changes as low as about 100 pg/mm².
19 The vapor diffusion rate into and out of the polymer film is generally rapid, but does depend upon the thickness of
20 the polymer film.

21 [0036] Sensor selectivity, the ability to detect a chemical species in an environment containing other
22 chemical species, is generally determined by the ability of the coated layer to specifically sorb the species to be
23 detected to the exclusion of almost all others. For most coatings, selectivity is obtained based on providing stronger
24 chemical interactions between the coated layer and the target species than occurs between the layer and species that
25 are not to be detected. The method of selectively detecting the presence of a chemical entity within an environment
26 comprises (a) placing the sensing portion of the device of the invention in the environment and (b) detecting changes
27 in the coated layer of the sensing portion of the device. The environment may be gaseous or liquid.

28 [0037] More than one device may be provided. For example, a plurality of sensor portions could be used
29 in a sensor array with, e.g., associated control devices and software, in a manner similar to conventional procedures
30 employing sensor arrays.

31 [0038] After an initial sensing has taken place, the coated sensor layer can be purged or cleaned by a
32 second stream, allowing the sensing of a new third stream to take place. For example, for liquid sensing
33 applications, water- or acid-base solutions could be used as purging or cleaning solutions, depending upon the
34 species being detected and the nature of the layer. For gas applications, dry nitrogen or clean air could be used as a
35 cleaning stream.

36 [0039] In the devices and methods of the invention, the compounds are good sorbents for basic vapors,
37 such as organophosphorus and nitro-substituted compounds. It is expected that the devices of the invention could

1 weigh about 0.25 to 5 pounds and could, therefore, be easily mounted on a remote or robotic vehicle for
2 automatically detecting toxic chemicals or buried explosives or munitions. Alternatively, such a device would also
3 be useful for remotely detecting explosives vapors emitting from a person intending the destruction of private
4 property and/or personnel, such as, for example, at crowded public places like airports or arenas where terrorist
5 activity may be suspected.

6 [0040] If desired, it is possible to increase the concentration of explosive vapors contained in the area
7 being monitored, i.e., speed up their release from buried or otherwise hidden munitions or explosives, by irradiating
8 the area with electromagnetic radiation. For example, a beam-forming antenna could be employed to direct high
9 frequency to long wavelength microwave radiation at the area suspected of containing buried munitions, such as
10 landmines. This will gently warm the area being checked and increase explosive vapor leakage prior to testing with
11 the device of the invention. Increasing the concentration of vapor in the soil or other environment surrounding a
12 munition will produce a stronger signal following the reaction with the sensor portion of the device of the invention.

13 [0041] The chemoselective, hyperbranched compounds of the invention exhibit high selectivity and
14 sensitivity toward hydrogen bond basic vapors, due to the sensitivity and selectivity of the halogen substituted
15 alcohol or phenol functional groups that are present. The functionalized hyperbranched compounds of the invention
16 also have the advantage of high-yield preparation methods, ready purification, in addition to having an increased
17 availability of functional groups to analytes, as compared with linear polymeric coatings. Moreover, the flexibility
18 in the synthesis of these materials allows one to tailor a wide variety of related chemoselective hyperbranched
19 compounds.
20

21 EXAMPLES

22 [0042] Unless otherwise noted, all synthetic procedures were carried out under inert atmosphere using
23 standard Schlenk and vacuum line techniques. Solvents were dried and degassed under an argon atmosphere using
24 appropriate drying agents.

25 [0043] These examples are intended to illustrate the present invention to those skilled in the art and
26 should not be interpreted as limiting the scope of the invention set forth in the claims.
27

28 Example 1 – Preparation of $[-CH_2-Si(CH=CH_2CH_2CH_2C(CF_3)_2OH)_2-]_n$

29 [0044] To a 500 mL flask containing 2.1 g of Mg chips was added 30 mL of freshly distilled THF. The
30 resulting mixture was cooled to 0 °C and treated with 10 mL (14.65 g) of $ClCH_2SiCl_3$ via syringe. The reaction
31 mixture was stirred at 0 °C for four hours with an additional 60 mL of THF being added in portions as needed to
32 keep the solution from getting too thick due to salt formation. The reaction mixture was then stirred for 2 hours at
33 room temperature and treated dropwise with allylmagnesium bromide (162 mL of 1.0 M in ether) over a two hour
34 period. The resulting solution was stirred at room temperature for 20 hours. The reaction was then quenched with
35 saturated aqueous NH_4Cl and the organic portion extracted with diethyl ether, dried over $MgSO_4$, and filtered
36 through 1 cm of SiO_2 . Removal of the volatiles left the product polymer as a pale yellow, viscous oil. A sample of
37 the parent polymer (2.0 g) was dissolved in $CHCl_3$ (30 mL) and placed into a mild steel cylinder along with a

magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone (~ ±4.0 g) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours. The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was filtered through Celite and the volatiles removed to give a pale brown polymer. FTIR (NaCl, cm⁻¹) showed the characteristic OH stretch (~3510 cm⁻¹) verifying the presence of the -C(CF₃)₂OH groups in the functionalized product.

Example 2 – Preparation of [-CH₂-Si{CH₂CH₂CH₂C₆H₃(C(CF₃)₂OH)₂}]_n

[0045] To a 500 mL flask containing 7.0 g of Mg chips was added 20 mL of freshly distilled THF. The resulting mixture was cooled to 0 °C and treated with 10 mL (14.65 g) of ClCH₂SiCl₃ via syringe. The reaction mixture was stirred at 0 °C for four hours with an additional 60 mL of THF being added in portions as needed to keep the solution from getting too thick due to salt formation. The reaction mixture was stirred for 2 hours at room temperature then cooled to 0 °C and treated drop-wise with a THF (60 mL) solution of (3-bromopropyl)benzene (25.5 mL) over a two hour period. The reaction mixture was then allowed to warm with occasional cooling to maintain the temperature below 40 °C. The resulting solution was stirred at room temperature for 20 hours. The reaction was then quenched with saturated aqueous NH₄Cl and the organic portion extracted with diethyl ether, dried over MgSO₄, and filtered through 1 cm of SiO₂. Removal of the volatiles left the product polymer as a pale yellow, viscous oil. A sample of the parent polymer (2.0 g) was mixed with a catalytic amount of AlCl₃ (0.1 g) and placed into a mild steel cylinder along with a magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone (~ 4.0 g) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours. The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was washed with water, dried over MgSO₄, filtered through Celite and the volatiles removed to give a pale brown viscous oil. FTIR (NaCl, cm⁻¹) showed an OH stretch (~3510 cm⁻¹) verifying the presence of the -C(CF₃)₂OH groups in the functionalized product.

Example 3 – Preparation of [-CH₂-Si{CH₂CH=CHC₆H₃(C(CF₃)₂OH)₂}]_n

[0046] To a 500 mL flask containing 7.0 g of Mg chips was added 20 mL of freshly distilled THF. The resulting mixture was cooled to 0 °C and treated with 10 mL (14.65 g) of ClCH₂SiCl₃ via syringe. The reaction mixture was stirred at 0 °C for four hours with an additional 60 mL of THF being added in portions as needed to keep the solution from getting too thick due to salt formation. The reaction mixture was stirred for 2 hours at room temperature then cooled to 0 °C and treated dropwise with a THF (60 mL) solution of cinnamyl bromide (33.0 g) over a six hour period. The resulting solution was stirred at room temperature for 20 hours. The reaction was then quenched with saturated aqueous NH₄Cl and the organic portion extracted with diethyl ether, dried over MgSO₄, and filtered through 1 cm of SiO₂. Removal of the volatiles left the product polymer as a yellow, viscous oil. A sample

of the parent polymer (2.0 g) was mixed with a catalytic amount of AlCl_3 (0.1 g) and placed into a mild steel cylinder along with a magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone (~ 4.5 g) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours. The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was washed with water, dried over MgSO_4 , filtered through Celite and the volatiles removed to give a pale brown viscous oil. FTIR (NaCl , cm^{-1}) showed an OH stretch (~3510 cm^{-1}) verifying the presence of the $-\text{C}(\text{CF}_3)_2\text{OH}$ groups in the functionalized product.

Example 4 – Preparation of $[-(\text{CH}_2)_2-\text{Si}(\text{CH}_2\text{Si}(\text{CH}=\text{CHCH}_2\text{C}(\text{CF}_3)_2\text{OH}))_3]_n$

[0047] To a 500 mL flask containing 6.0 g of Mg chips was added 20 mL of freshly distilled THF. The resulting mixture was cooled to 0 °C and treated with 10.0 mL (16.69 g) of $\text{BrCH}_2\text{CH}_2\text{SiCl}_3$ via syringe. The reaction mixture was stirred at 0 °C for four hours with an additional 60 mL of THF being added in portions as needed to keep the solution from getting too thick due to salt formation. The reaction mixture was stirred for 2 hours at room temperature then cooled to 0 °C and treated dropwise with a THF (50 mL) solution of chloromethyl-triallylsilane (26.0 g) over a four hour period. The resulting solution was stirred at room temperature for 24 hours. The reaction was then quenched with saturated aqueous NH_4Cl and the organic portion extracted with diethyl ether, dried over MgSO_4 , and filtered through 1 cm of SiO_2 . Removal of the volatiles left the product polymer as a yellow, viscous oil. A sample of the parent polymer (2.0 g) was dissolved in CHCl_3 (30 mL) and placed into a mild steel cylinder along with a magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone (~ 4.5 g) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours. The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was washed with water, dried over MgSO_4 , filtered through Celite and the volatiles removed to give a pale brown viscous oil. FTIR (NaCl , cm^{-1}) showed an OH stretch (~3510 cm^{-1}) verifying the presence of the $-\text{C}(\text{CF}_3)_2\text{OH}$ groups in the functionalized product.

Example 5 – Preparation of $[-(\text{CH}_2)_3-\text{Si}(\text{CH}=\text{CHCH}_2\text{C}(\text{CF}_3)_2\text{OH})_2]_n$

[0048] To a 50 mL flask was added triallylsilane (2.1 g) and tetraallylsilane (0.1 g) along with 1-2 drops of 0.1 mM $\text{H}_2\text{PtCl}_6(\text{H}_2\text{O})_x$ in THF. The resulting mixture was stirred at 50 °C for 18 hours resulting in a viscous pale yellow oil. The reaction mixture was dissolved in 20 mL of hexanes and filtered through 1 cm of SiO_2 . Removal of the volatiles left the product polymer as a pale yellow, viscous oil. A sample of the parent polymer (1.0 g) was dissolved in CHCl_3 (20 mL) and placed into a mild steel cylinder along with a magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone (~ 3.0 g) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours.

The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was filtered through Celite and the volatiles removed to give a pale brown polymer. FTIR (NaCl, cm^{-1}) showed the characteristic OH stretch ($\sim 3510 \text{ cm}^{-1}$) verifying the presence of the $-\text{C}(\text{CF}_3)_2\text{OH}$ groups in the functionalized product.

Example 6 – Preparation of $[-(\text{CH}_2)_3-\text{Si}(\text{CH}_2\text{CH}_2\text{CH}_2\text{C}_6\text{H}_3(\text{C}(\text{CF}_3)_2\text{OH})_2)(\text{CH}=\text{CHCH}_2\text{C}(\text{CF}_3)_2\text{OH})-]_n$

[0049] To a 50 mL flask was added 3-phenylpropyldiallylsilane (3.1 g) and allylbenzene (0.05 g) along with 1-2 drops of 0.1 mM $\text{H}_2\text{PtCl}_6(\text{H}_2\text{O})_x$ in THF. The resulting mixture was stirred at 50 °C for 22 hours resulting in a viscous pale yellow oil. The reaction mixture was dissolved in 20 mL of hexanes and filtered through 1 cm of SiO_2 . Removal of the volatiles left the product polymer as a pale yellow, viscous oil. A sample of the parent polymer (1.5 g) was dissolved in CHCl_3 (30 mL) and placed into a mild steel cylinder along with a magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone ($\sim 3.5 \text{ g}$) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours. The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was filtered through Celite and the volatiles removed to give a pale brown polymer. FTIR (NaCl, cm^{-1}) showed the characteristic OH stretch ($\sim 3510 \text{ cm}^{-1}$) verifying the presence of the $-\text{C}(\text{CF}_3)_2\text{OH}$ groups in the functionalized product.

Example 7 – Preparation of $\text{co}-[-(\text{CH}_2)_3-\text{Si}(\text{CH}_2\text{CH}_2\text{CH}_2\text{C}_6\text{H}_3(\text{C}(\text{CF}_3)_2\text{OH})_2)-]_m-[-(\text{CH}_2)_3\text{Si}(\text{CH}=\text{CHCH}_2\text{C}(\text{CF}_3)_2\text{OH})_2-]_n$

[0050] To a 50 mL flask was added 3-phenylpropyldiallylsilane (1.8 g), triallylsilane (2.5 g) and tetraallylsilane (0.1 g) along with 1-2 drops of 0.1 mM $\text{H}_2\text{PtCl}_6(\text{H}_2\text{O})_x$ in THF. The resulting mixture was stirred at 50 °C for 20 hours resulting in a viscous pale yellow oil. The reaction mixture was dissolved in 20 mL of hexanes and filtered through 1 cm of SiO_2 . Removal of the volatiles left the product polymer as a pale yellow, viscous oil. A sample of the parent polymer (1.5 g) was dissolved in CHCl_3 (30 mL) and placed into a mild steel cylinder along with a magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone ($\sim 4.0 \text{ g}$) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours. The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was filtered through Celite and the volatiles removed to give a pale brown polymer. FTIR (NaCl, cm^{-1}) showed the characteristic OH stretch ($\sim 3510 \text{ cm}^{-1}$) verifying the presence of the $-\text{C}(\text{CF}_3)_2\text{OH}$ groups in the functionalized product.

Example 8 – Preparation of co-[Si{CH₂CH₂CH₂Si(CH₂CH₂CH₂C₆H₅(C(CF₃)₂OH)₂)

[CH₂CH₂CH₂Si(CH₂CH₂CH₂C₆H₅(C(CF₃)₂OH)₂)(CH=CHCH₂C(CF₃)₂OH)_{2-x}(CH₂CH₂CH₂)_{x-2}}]₄[-(CH₂)₃-
Si(CH=CHCH₂C(CF₃)₂OH)₂]_n

[0051] To a 100 mL flask was added triallylsilane (2.5 g) and the dendrimeric polymer Si{CH₂CH₂CH₂Si(CH₂CH₂CH₂C₆H₅)[CH₂CH₂CH₂Si(CH₂CH₂CH₂C₆H₅)(CH₂CH=CH₂)₂]₂}]₄(0.20 g) along with 1-2 drops of 0.1 mM H₂PtCl₆(H₂O)_x in THF. The resulting mixture was stirred at 50 °C for 24 hours resulting in a viscous pale yellow oil. The reaction mixture was dissolved in 20 mL of hexanes and filtered through 1 cm of SiO₂. Removal of the volatiles left the product polymer as a pale yellow, viscous oil. A sample of the parent polymer (1.0 g) was dissolved in CHCl₃ (30 mL) and placed into a mild steel cylinder along with a magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone (~ 3.0 g) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours. The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was filtered through Celite and the volatiles removed to give a pale brown polymer. FTIR (NaCl, cm⁻¹) showed the characteristic OH stretch (~3510 cm⁻¹) verifying the presence of the -C(CF₃)₂OH groups in the functionalized product.

Example 9 – Preparation of co-[-(CH₂)₃-Si(Me)O-]_m[-(CH₂)₃-Si(CH=CHCH₂C(CF₃)₂OH)₂]_n

[0052] To a 100 mL flask was added triallylsilane (3.0 g), tetraallylsilane (0.05 g) and poly(methylhydrosiloxane) (0.15 g) along with 1-2 drops of 0.1 mM H₂PtCl₆(H₂O)_x in THF. The resulting mixture was stirred at 50 °C for 24 hours resulting in a viscous pale yellow oil. The reaction mixture was dissolved in 20 mL of hexanes and filtered through 1 cm of SiO₂. Removal of the volatiles left the product polymer as a pale yellow, viscous oil. A sample of the parent polymer (1.0 g) was dissolved in CHCl₃ (30 mL) and placed into a mild steel cylinder along with a magnetic stir bar. The steel cylinder was then cooled in liquid nitrogen and evacuated. Hexafluoroacetone (~ 3.0 g) was introduced into the steel cylinder via vacuum transfer. The cylinder was sealed, removed from the vacuum line, and heated to 65 °C for 48 hours. The cylinder was then cooled to room temperature and the volatiles removed under vacuum. Once evacuated, the reaction cylinder was opened to the air, and the hyperbranched compound inside was extracted with chloroform (4 x 30 mL). The resulting solution was filtered through Celite and the volatiles removed to give a pale brown polymer. FTIR (NaCl, cm⁻¹) showed the characteristic OH stretch (~3510 cm⁻¹) verifying the presence of the -C(CF₃)₂OH groups in the functionalized product.

Example 10 - Applying a Thin Film to a SAW Device

[0053] SAW devices are cleaned in a Harrick plasma cleaner prior to polymer film application. Spray-coated films of the compound of Fig. 1 in chloroform (1% by weight) are applied to a SAW device using an airbrush supplied with compressed dry nitrogen. The frequency change of the SAW device operating in an oscillator circuit is monitored during deposition, using the change in frequency, typically about 250 kHz, as a measure of the amount of material applied. After application, the films are optionally annealed in an oven at 50°C overnight. Spray-coated

1 films are examined by optical microscopy with a Nikon microscope using reflected light Nomarski differential
2 interference contrast.

3
4 Example 11:- Detection of Basic Vapors with a Compound-Coated SAW Device

5 [0054] The compounds of Figures 1 and 2 are separately applied to SAW devices and tested against
6 organic vapors at various concentrations. Upon exposure to a vapor, the coated acoustic wave devices undergo a
7 shift in frequency that is proportional to the concentration of the vapor. Times to steady state response,
8 corresponding to equilibrium partitioning of the vapor into the compound layer, are typically under 10 seconds using
9 a vapor delivery system. From frequency shift data for a vapor at multiple concentrations, calibration curves are
10 constructed. The calibration curves are generally linear at moderate concentrations, but deviate from linearity at the
11 high and low concentration levels. Linear calibration curves are consistent with hydrogen-bonding interactions at a
12 finite number of sites in the compound.

13
14 Example 12:- Coating a Capillary Column

15 [0055] A solution of the compound of Fig. 2 in chloroform is used to coat the interior surface of several
16 one-meter silica capillary columns with an inside diameter of 100 microns. The procedure to coat a 100-micron i.d.
17 column from Fused Silica Intermediate Polarity (part number 2-5745, Supelco, Pennsylvania) involves filling the
18 capillary with a solution of the compound, closing one end of the capillary, and pulling a vacuum off the other end
19 of the capillary at a fixed temperature. The solution-filled column is placed into a gas chromatographic oven
20 stabilized at 30°C to control the temperature. A vacuum is then pulled using an oil-free Teflon-coated diaphragm
21 pump (Fisher part number 13-875-217C), with a vacuum of -70 kPa, typically being applied for about 15-20 hours.

22 [0056] The thickness and thickness uniformity are verified by cutting a coated column into several pieces
23 and looking at the cross sections using a high power optical microscope. The thickness of one micron is usually in
24 good agreement with the theoretical film thicknesses.

25
26 Example 13:- Optical Fiber Drawing and Cladding

27 [0057] The compound of Fig. 2 is combined with a solvent to form a viscous mixture, which is stirred
28 until well-blended and degassed under vacuum. The viscous mixture is applied to a fused silica fiber as it is freshly
29 drawn from a Heathway fiber drawing apparatus through a 2-5 mm Sandcliff cladding cup, and into a 45 cm long
30 clamshell furnace for curing. The viscous mixture is supplied to the cladding cup under a pressure of about 0.8 to
31 about 1.5 psi. The optimal furnace temperature and fiber draw-speed are typically about 520 °C and 8-9 m/min,
32 respectively. These relatively slow draw rates are usually used for manual control of the drawing conditions, but
33 sometimes result in variable core diameters and coating thickness. However, when used with the other conditions
34 described, a fairly uniform coating that is light yellow in color and slightly tacky to the touch is usually obtained. As
35 the viscosity of the solution of the compound increases during the fiber drawing, the delivery pressure should be
36 increased over the course of filling, usually about two hours.

1 [0058] Half-meter to one-meter sections are hand selected for quality. The best fiber sections made under
2 these conditions have a smooth coating of about 25 microns thick over a 180-micron diameter core. All are usually
3 effective in guiding light.

4 [0059] Additional advantages and modifications will readily occur to those skilled in the art. Therefore,
5 the invention in its broader aspects is not limited to the specific details and representative embodiments shown and
6 described herein. Accordingly, various modifications may be made without departing from the spirit or scope of the
7 general inventive concept as defined by the appended claims and their equivalents.
8

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2